

PRODUCT DATA

<u>Properties</u>	<u>Method</u>	<u>Specifications</u>
Concealing point	ASTM D 3104	102 - 108 °C
Penetration at 25 °C	ASTM D 1321	0 - 4 *0.1mm
Viscosity at 160 °C	ASTM D 3236	3200 - 4000 Mpa.s
Shape		pallets
Color	visible	yellow / brown
Advised mixture with Bitumen 80-100		15 - 20%

EFFECTS ON BITUMEN

%-addition		0	18
Bitumen 80/100		100	82
Concealing point *1		50 °C	78 °C
Penetration *2	25 °C	76-80	26
	40 °C	> 300	80
Viscosity	140 °C	365 Mpa.s	1250 Mpa.s
	160 °C	140 Mpa.s	450 Mpa.s
	180 °C	70 Mpa.s	220 Mpa.s

We reserve the right to change the specifications as a result of technical progress or for reasons related to production.
No guarantee or warranty is implied as to any particular applications of our products.

Important notice to purchaser:

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price.