

**DESCRIPTION**

Bitumen Modifier (wax based 100% Solids)

**TYPICAL PROPERTIES**

	<u>Typical value</u>	<u>Units</u>	<u>Standard</u>
Melting Piont	70	°C	DIN 51 570
Specific Gravity @ 70°C	0,78	kg/dm3	DIN 51 757
Solid Content %	100	%	N.A.
Colour Liquid	≤ 1	Gardner	ASTM D1544
Colour Solid	White	N.A.	Visual
Flash Point	210	°C	DIN 51 376
Viscosity @ 100°C	5,9	mm2/s	DIN 51 562/T1
Congeaing Point	68-72	°C	DIN ISO 2207
Penetration	9-16	0,1 mm	DIN 51 579
Oil Content	≤ 0,5	%	DIN ISO 2908
Odour	Odourless	N.A.	N.A.
Boiling Piont	370	°C	DIN 51 751

**SAFETY PRECAUTIONS**

Please refer to the material safety data sheet (MSDS).

**STORAGE & STABILITY**

Store in a dry and cool location at ambient room temperature.  
Shelf life is ≥2 years.

**DOSAGE IN BITUMEN**

2-4 m/m% of total bitumen level.

**DOSAGE IN ASPHALT MIXER**

During or just after bitumen dosing. 5 to 10 seconds longer wet mixing.

**Important notice to purchaser:**

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. Limitation of liability and remedy: Purchase or use of these products constitutes an agreement with seller and manufacturer that, if the product proves to be defective or unsuitable, seller's and manufacturer's liability and the exclusive remedy, regardless of tort or contract theory or of incidental or consequential damages shall be to receive, at seller's or manufacturer's option, an equivalent quantity of replacement product or a refund of the purchase price.